

PU PRIMER WHITE

General Description:

PU PRIMER WHITE is a polyurethane pigmented undercoat based on saturated polyfunctional polyesters and selected pigments. A two-component material with outstanding characteristics, filling well pores of all types of woods. It has good sanding qualities, which reduces the number of coats required.

Major Uses:

PU PRIMER WHITE sets, turned pieces.

Characteristics and Physical Properties:

Appearance White liquid Specific Gravity 1.5 kg/L Viscosity @ 25°C 35-40 poise Flash Point 21°C Non-volatile Base : 76 % Catalyst : 24% Application condition: Air temperature 5 ~ 35°C Relative humidity 85% max Application method Auto / conventional spray Recommended Catalyst # 004
Viscosity @ 25°C 35-40 poise Flash Point 21°C Non-volatile Base : 76 %
Flash Point 21°C Non-volatile Base: 76 % Catalyst: 24% Application condition: Air temperature 5 ~ 35°C Relative humidity 85% max Application method Auto / conventional spray
Non-volatile Base: 76 % Catalyst: 24% Application condition: Air temperature Fig. 10 conventional Spray
Catalyst : 24% Application condition: Air temperature
Application condition: Air temperature 5 ~ 35°C Relative humidity 85% max Application method Auto / conventional spray
Air temperature 5 ~ 35°C Relative humidity 85% max Application method Auto / conventional spray
Relative humidity 85% max Application method Auto / conventional spray
Application method Auto / conventional spray
spray
Recommended Catalyst # 004
· · · · · · · · · · · · · · · · · · ·
catalyst
Thinner # 105/205
Mixing ratio(%wt.) Base : Catalyst:
Spray visc. = 13~15" Thinner
100 50 20-25
Pot life@25°C 2~3 hours
Drying time:
Dust free 20 – 30 min.
Touch free 35 – 45 min.
Recoat 2 - 3 hours
Hard 48 - 72 hours
Sandable 2 – 3 hours
Coverage 8 m ² /L (150 g/m ²)

Method of Application:

- To the surface well prepared, apply 1 − 2 coats of PU PRIMER WHITE with Catalyst # 004, vertically and horizontally.
- Fill all cracks, deep holes and joints with polyester putty.
- Sand the surface with medium grade sand paper.
- Apply 1 2 coats of PU PRIMER WHITE prior to the final sanding and top coating.
- In case PU PRIMER WHITE is used in curtain coating, the viscosity of the lacquer should be carefully controlled and monitored for continuity of the finish.
- Recoating must be done within 3 minutes to 3 hours maximum. Medium sanding with 240-320 grit sandpaper is recommended prior to any subsequent coatings

Packing:

Available in 1Usg, 20 lit. Pail and 200lit Drum.

Storage:

Shelf life 12 months minimum if stored below 25°C.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or PU Thinner # 105.

Physiological Hazards:

PU PRIMER WHITE and Catalyst # 004 do not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. PU PRIMER WHITE is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advise.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.