

Thinners

InnoColor Thinners

Product Description

Used to reduce application viscosity and to increase the smoothness of the paint film. Thinner with high dissolving ability, compatible with InnoColor primers, basecoats, topcoats and clears.




IC - 940 Thinner 5°C - 15°C (Fast) IC - 950 Thinner 15°C - 25°C (Standard) IC - 960 Thinner 25°C - 35°C (Slow)
IC - 970 Thinner >35°C (Extra Slow)

Technical Characteristics

Color: Transparent Shelf life: 48 months at 25°C

Pre-treatment

As specified in the TDS of the products in which IC Thinner is being used.

	Mixing Ratio	<p>Stir well before use.</p> <table border="0"> <tr> <td>IC - 981 Primer</td> <td>100 (vol)</td> <td>100 g</td> </tr> <tr> <td>IC - 961 Hardener</td> <td>25 (vol)</td> <td>20 g</td> </tr> <tr> <td>IC - 940/950/960/970 Thinner</td> <td>50 - 60 (vol)</td> <td>30 - 35 g</td> </tr> <tr> <td>2K Solids/Clears</td> <td>100 (vol)</td> <td>100 g</td> </tr> <tr> <td>IC - 940/950/960/970 Thinner</td> <td colspan="2">depending on 2K Solids/Clears</td> </tr> </table>	IC - 981 Primer	100 (vol)	100 g	IC - 961 Hardener	25 (vol)	20 g	IC - 940/950/960/970 Thinner	50 - 60 (vol)	30 - 35 g	2K Solids/Clears	100 (vol)	100 g	IC - 940/950/960/970 Thinner	depending on 2K Solids/Clears	
IC - 981 Primer	100 (vol)	100 g															
IC - 961 Hardener	25 (vol)	20 g															
IC - 940/950/960/970 Thinner	50 - 60 (vol)	30 - 35 g															
2K Solids/Clears	100 (vol)	100 g															
IC - 940/950/960/970 Thinner	depending on 2K Solids/Clears																
	Mixing Ratio	<table border="0"> <tr> <td>1K Basecoats</td> <td>100 (vol)</td> <td>depending on colors</td> </tr> <tr> <td>IC - 940/950/960/970 Thinner</td> <td>100 - 120 (vol)</td> <td></td> </tr> </table> <p>Mix well and strain before application. Note: If the temperature and humidity are too high, IC - 70 retarder solvent can be added.</p>	1K Basecoats	100 (vol)	depending on colors	IC - 940/950/960/970 Thinner	100 - 120 (vol)										
1K Basecoats	100 (vol)	depending on colors															
IC - 940/950/960/970 Thinner	100 - 120 (vol)																
	Application	<p>As specified in the TDS of the products in which IC Hardeners are being used. Important: Due to different dissolving ability, it is recommended InnoColor products should be used with IC Thinner to ensure the best performance.</p> <p>Tips:</p> <ol style="list-style-type: none"> 1) Be cautious of over dissolution of the paint when using high - dissolving thinner. Avoid orange peel. 2) Be cautious of under dissolution of the paint when using poor - dissolving thinner. Avoid poor leveling and poor color effect (e.g. orientation of aluminum/pearl particles, poor solid color brightness). 															

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.