Sultanate of Oman.

Tel: +968 24446218, Fax: +968 24446962 E-mail: Sadolin.Oman@akzonobel.com

Technical Data Sheet



Levis Gold

Product Code - F97LVGOLD

Product Description

Levis Gold is a solvent based, Metallized paint which is Gold

in colour.

Designed for interior use only.

Advantages

Excellent decorative interior product with strong Gold

metallized appearance, for use on woodwork, metal frames

and wall surfaces.

Typical Uses

Levis Gold can be applied to woodwork & Derivatives, plaster & derivatives, as well as ferrous and non-ferrous metals.

Surfaces should be treated with an appropriate primer or coated over, old, clean and de-polished surfaces.

Technical

Colours Gold

Finish Metallized Finish, Semi-Gloss

Volume Solids $\% \pm 2\%$ $38 \pm 2\%$ Typical WFT (microns)26Typical DFT (microns)10

Theoretical Spreading Rate m²/lt 16 - 20 m²/ litre (Dependent on Substrate, Application

Method, Application Conditions and System)

Specific Gravity 1.18 ± 0.02

Pack Sizes 0.125 LT, 0.250 LT, 0.500 LT, 0.750 LT

Flash Point Above 34°C VOC 716 Gms/Ltr

Storage Store away from sunlight in a covered, cool and dry

Shelf Life environment 2 Years

Drying/Over coating Information

°C Touch Dry Hard Dry Overcoating @ 25°c 30 Min 1 Hr 1 - 4 Hrs*

* Product should be applied in 1 coat, if over coating is

required please do so within these times.

Application and Use

Application Methods

Brush Use a Natural bristled Brush

Use a Medium Pile Polyester Roller for Smooth

Spray: Conventional Spray

Thinner

For Mixing Ready for use.
For Cleaning Use Thinner 8300896

Spray Recommendations

Conventional Yes Airless Spray No Akzo Nobel Oman SAOC P.O. Box 531, Ruwi, Postal code 112 Sultanate of Oman. Tel: +968 24446218, Fay: +968 2444694

Tel: +968 24446218, Fax: +968 24446962 E-mail: Sadolin.Oman@akzonobel.com



Technical Data Sheet

Levis Gold

Product Code - F97LVGOLD

Surface Preparation

New uncoated surfaces

The surface to be primed should be well cured. Ideally the moisture content of the substrate should be less than 16% with a pH between 8 & 9.

Previously coated

The surface to be painted should be free from dust, grease, oil and should not be flaky. Primer is required only where the previously painted surface is removed, exposing the bare surface. In areas where multiple coats from previous applications are present, it is best to remove coatings to come to the barest surface possible. In case the surface is infested with mould or fungus thorough cleaning followed by treatment with an anti-fungal solution is recommended. The surface treated for the fungus or moulds should be thoroughly washed, dried and mopped prior to application

Special Surfaces

In cases where the surface temperature exceeds 35° C, wet the surface with water prior to application of primer, allowing sufficient time for the water to dry leaving the surface moist.

Health Safety & environment

Store can upright with lid tightly closed in a dry area with good ventilation away from ignition sources. Keep out of reach of children and away from food and drink. Do not use empty paint containers to store food. Harmful if ingested. If ingested seek immediate medical attention. Do not breathe spray mist or dust from sanding. Use appropriate protection. In case of contact with eyes, rinse immediately with clean water and if irritation persists, seek medical attention. Avoid contact with skin by using appropriate protection. Contact with skin can cause irritation. Splashes can be removed from skin by using soap & clean water. Do not pour left over paint down drains or into watercourses. Dispose of empty containers as per local regulations. Material Safety datasheet can be made available on request.

Disclaimer: The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to law) any loss or damage arising out of the use of the product. All products supplied and technical avice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local AkzoNobel Oman SAOC representative that this data sheet is current prior to using the product.

Akzo Nobel Oman SAOC, P.O. Box 531, Ruwi, Postal code 112 Sultanate of Oman. Tel: +968 24446218, Fax: +968 24446962

