

COPRABEL S.A Z.I. Wavre-Nord, Avenue Lavoisier, 7 BE-1300 Wavre Belgium
Tel: +32 10 23 82 80 Fax:+32 10 23 82 89 www.coprabel.com info@coprabel.com



# **TECHNICAL DATA SHEET**

## EASY COLOR® METALLIC SPRAY PAINT

### **DESCRIPTION**

Highly glossy opacifying and quick-drying golden solvent-based spray paint offering a - *mirror effect* – and a good adhesion, for decorative and artistic design of interior elements in wood, metal, aluminum, glass and various types of plastics. Available in different shades.

#### **PRECAUTIONS**

- Shake before use.
- Avoid contact with eyes and skin.
- Avoid breathing dust/ fume/ gas/ mist/vapours/ spray.
- Wear protective clothes, mask, glasses and gloves.
- Keep out of reach of children.
- Keep products away from frost and from heat sources.
- Do not dispose of residual paint by flushing it away.
- Take appropriate precaution when disposing of the packages.
- · Consult the Safety Data Sheet for more details.

#### METHOD OF USE

Surface preparation	Sand and clean the substrate, dry and remove any grease. For porous surfaces, apply a suitable primer.	
Application	Wear safety gloves and spray mask.  Before use, shake for 2 minutes and do a test. Protect the surrounding area. Vaporization distance: 25-30 cm from the substrate. Apply several thin cross layers. Shake the spray can between the layers. Do not cover with matt varnish to keep the mirror and shiny effect. Ideal application temperature: 15-25°C.	
Drying time	Touch dry at 20°C: +/- 10 min. Fully hardened: after 12 hours.	
Cleaning of Material	Self-cleaning valve (no need to empty the tube valve).	
Shelf life	Minimum 5 years in original tightly closed aerosol.	



COPRABEL S.A Z.I. Wavre-Nord, Avenue Lavoisier, 7 BE-1300 Wavre Belgium Tel: +32 10 23 82 80 Fax:+32 10 23 82 89 www.coprabel.com info@coprabel.com



# **TECHNICAL DATA SHEET**

## EASY COLOR® METALLIC SPRAY PAINT

#### **TECHNICAL SPECIFICATIONS**

Aspect	Metallic high gloss, mirror effect.		
Composition	Binder:	synthetic resin.	
	Pigment:	bronze powder.	
	Propellant agent:	Light Gas - propane/butane	
Thickness Dry Film	Approximately 10-15 μm.		
Flash Point	Below 21°C.		
Indicative Coverage	+/- 1,5 m² per can (+/- 3,7 m²/L per coat),		
	depending on the thickness of the layer applied.		
	For an enhanced effect, apply a 2nd coat.		
Packaging	Aerosol can 400 ML (16 oz).		

### **REMARKS AND RECOMMENDATIONS**

Pressurized container. Store in a well-ventilated and dry room at temperatures between 15°C and 50 °C. Protect from sunlight. Do not pierce or burn, even after use., Do not spray on a naked flame or any incandescent material., Keep away from sources of ignition - No smoking.

Keep container tightly closed. Store carefully closed containers upright to prevent any leaks.

Warranty invalid if other system than provided by COPRABEL S.A. is used.

Note: Cancels and replaces the former editions. It's up to our customers to check, before application, if it is indeed the latest edition. The information contained in this note has only one indicative range and cannot compensate a description suitable with the nature and the state of surface to be treated.