

PU FLEXICOAT # 5200 CLEAR

General Description:

PU FLEXICOAT is a polyurethane lacquer, particularly formulated for varnishing indoor/outdoor furniture, offering a very high flexibility and outstanding resistance to abrasion and UV protection.

Major Uses:

PU FLEXICOAT is highly recommended for external treatment of high quality woods. It is formulated to create a surface which require high resistance to abrasion caused by extreme weather condition in marine environment.

Characteristics and Physical Properties:

Appearance Transparent liquid Code 5200 Specific gravity 0.970 kg/L Gloss Gloss/semigloss/matt Viscosity (FC#4) 26" Flash point 20°C Non-volatile (wt%) 37-40 Catalyst Catalyst # 085 Application condition Air temperature Relative humidity 85% max. Application method Brush / Spray Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) 3-4 hours Drying time (25°C) Dust free 35 - 45 min. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate 8-10 m²/L Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours. Basecoat PU Flexiseal 5051	Ondi dotteriotioo di	ia i frysical i roperties.
Specific gravity Gloss Gloss/semigloss/matt Viscosity (FC#4) Flash point Non-volatile (wt%) Catalyst Application condition Air temperature Relative humidity Application method Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) Dust free 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Appearance	Transparent liquid
Gloss Gloss/semigloss/matt Viscosity (FC#4) 26" Flash point 20°C Non-volatile (wt%) 37-40 Catalyst Catalyst # 085 Application condition Air temperature Relative humidity 85% max. Application method Brush / Spray Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) 3-4 hours Drying time (25°C) Dust free 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate 8-10 m²/L Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Code	5200
Gloss Gloss/semigloss/matt Viscosity (FC#4) 26" Flash point 20°C Non-volatile (wt%) 37-40 Catalyst Catalyst # 085 Application condition Air temperature Relative humidity 85% max. Application method Brush / Spray Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) 3-4 hours Drying time (25°C) Dust free 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate 8-10 m²/L Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Specific gravity	0.970 kg/L
Flash point 20°C Non-volatile (wt%) 37-40 Catalyst Catalyst # 085 Application condition Air temperature Relative humidity 85% max. Application method Brush / Spray Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) 3-4 hours Pot life (25°C) 3-4 hours To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate 8-10 m²/L Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		Gloss/semigloss/matt
Non-volatile (wt%) Catalyst Application condition Air temperature Relative humidity Application method Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) Drying time (25°C) Dust free 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Viscosity (FC#4)	
CatalystCatalyst # 085Application condition Air temperature Relative humidity5~35°C 85% max.Application methodBrush / SprayThinnerPU Thinner 105 / 205Mixing ratio (%vol.)Base Catalyst Thinner 100 50 20-25Pot life (25°C)3-4 hoursDrying time (25°C)35 - 45 min.Dust free To touch To recoat Hard2 - 3 hrs.To recoat Hard6 - 12 hrs.Hard24 - 36 hrs.Coating rate8-10 m²/LRecoatingOne coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Flash point	20°C
Application condition Air temperature Relative humidity Application method Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) Drying time (25°C) Dust free To touch To recoat Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Non-volatile (wt%)	37-40
Air temperature Relative humidity Application method Thinner Mixing ratio (%vol.) Pot life (25°C) Dust free To touch To recoat Hard Recoating Coating rate Recoating Application method Brush / Spray PU Thinner 105 / 205 Base Catalyst Thinner 100 50 20-25 3-4 hours To an in. 2 - 3 hrs. 6 - 12 hrs. 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Catalyst	Catalyst # 085
Relative humidity Application method Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 50 20-25 Pot life (25°C) Drying time (25°C) Dust free 35 - 45 min. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Application condition	
Application method Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst 70-25 Pot life (25°C) Drying time (25°C) Dust free 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Air temperature	5~35°C
Thinner PU Thinner 105 / 205 Mixing ratio (%vol.) Base Catalyst Thinner 100 20-25 Pot life (25°C) Drying time (25°C) Dust free 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Relative humidity	
Mixing ratio (%vol.) Base 100 Sol 20-25 Pot life (25°C) 3-4 hours Drying time (25°C) 35 - 45 min. To touch 2 - 3 hrs. To recoat 6 - 12 hrs. Hard 24 - 36 hrs. Coating rate 8-10 m²/L Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
Pot life (25°C) Drying time (25°C) Dust free To touch To recoat Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Thinner	PU Thinner 105 / 205
Pot life (25°C) Drying time (25°C) Dust free To touch To recoat Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Mixing ratio (%vol.)	
Drying time (25°C) Dust free To touch To recoat Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
Dust free To touch To recoat Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		3-4 hours
To touch To recoat Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
To recoat Hard Hard 24 - 36 hrs. Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 - 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
Hard Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
Coating rate Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
Recoating One coat may be sufficient for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
for ordinary finish, however, one additional coat can be applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
one additional coat can be applied wet on wet if necessary. Light sanding with $400-600$ grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.	Recoating	
applied wet on wet if necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
necessary. Light sanding with 400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
400 – 600 grit sand paper is recommended before subsequent coat when recoating time exceed 3 hours.		
recommended before subsequent coat when recoating time exceed 3 hours.		
recoating time exceed 3 hours.		
hours.		subsequent coat when
		recoating time exceed 3
Basecoat PU Flexiseal 5051		hours.
•	Basecoat	PU Flexiseal 5051

Surface Preparation:

- Surface to be coated should be dry and clean.
- In the remaking of old wood and timber it is imperative to remove traces of wax, dust, dirt and other contaminants to ensure perfect adhesion.
- Solid woods that contain tannin oil must be treated with Isolator prior to the application of the Sealer.
- If the Isolator has been kept for drying in 12 hours, the coated surface must be sanded well for better anchorage.
- If stain is required, it is recommended to use External Wood Stain for outdoor exposure.
 Keep it dry for at least 12 hours prior to the application of appropriate sealer.

Application Procedure:

- The mixture ready for use, can be applied by brush, roller or spray. Apply 1 – 2 coats of P.U. Flexiseal prior to application of P.U. FLEXICOAT.
- Paint should be used within the pot life after components have been mixed together.
- Never leave drums of Catalyst open.

Storage:

Keep away from heat and fire. Store in the dark, cool and dry place. Shelf life up to 12 months in closed container.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or PU Thinner # 105 as soon as possible.

Packing:

Available in 1 USG, 20lit Pail

Precautions:

P.U. FLEXICOAT does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. PU FLEXICOAT is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.